

08-01-00

A

HENRY I. SCHANZER
ATTORNEY AT LAW
29 BROOKFALL ROAD
EDISON, NEW JERSEY 08817
TEL. (732) 572-3984
FAX (732) 572-3653

July 31, 2000

JC862 U.S. PTO
09/628908

07/31/00

Honorable Commissioner of Patents & Trademarks
Washington, D.C. 20231

Re: Kay 41-53-18-79-12
APPARATUS AND METHOD FOR SHAPING GLASS TUBES USING
AN INTERNAL MOLD

Dear Sir:

Enclosed herewith please find:

1. Transmittal Letter;
2. Application (Specification, Claims & Abstract - 27 pages);
3. Drawings - 8 sheets;
4. Declaration and Power of Attorney;
5. Assignment and Agreement; and
6. Assignment Recordation Sheet.

Thank you for your anticipated prompt attention to this matter.

Very truly yours,

Henry I. Schanzer
Henry I. Schanzer

I hereby certify that this paper and the documents referred to as attached therein are being deposited with the United States Postal Service on this date July 31, 2000 in an envelope as Express Mail EK467027615US addressed to Commissioner of Patents and Trademarks, Washington, D.C. 20231.

Henry I. Schanzer
Person Mailing the Paper

Henry I. Schanzer
Signature of person mailing Paper

JC820 U.S. PTO
07/31/00

09628908-073100

glass becomes too cool to form. As the required air pressure level increases, it becomes more difficult to complete the forming/molding operation before the glass cools. As a consequence, the heating/molding/air injection/ forming process must be repeated until the glass is finally formed/shaped as required. This subjects the process to errors, which is unacceptable. Elimination of the need to inject air is desirable as it eliminates the need for these multiple forming operations.

SUMMARY OF THE INVENTION

Applicants' invention resides, in part, in the recognition that the prior art methods for shaping the exhaust tube are directed primarily at applying shaping forces to the exterior portions of the exhaust tube. Applicants recognized that it is equally, if not more, important to directly control the shaping of the inner surface of the exhaust tube.

Accordingly, the present invention is directed to apparatus and methods for more accurately shaping the inner surface of the end portion of an exhaust tube selected to mesh with a starter tube. This includes the placement of an internal mold, or a "tool", within the selected end section of the tube selected to be shaped. The use of an "internal" mold reduces variations when using the present paddle, or pallet, method and it eliminates the need to inject air (and an end plug) when applying external molds to shape the tube.

The invention also includes a novel tool ("mold") for shaping the desired end section of a tube. In accordance with one aspect of the invention, the tool

001E20 805250
0962808 073100

("mold") has a variable configuration and may be selectively set to one configuration in which it is fully open or extended, or it may be set to another configuration in which it is closed or collapsed. When the tool is in its open, or extended, configuration, it functions as a mold and it then may be used to shape the inner surface of the tube. When the tool is in its closed, or collapsed, configuration, it is easily insertable into the tube or withdrawable from within the tube.

In accordance with one aspect of the invention, a collapsible tool is inserted into the end of an exhaust tube to be shaped. The collapsible tool can assume either a fully open, (i.e., extended) configuration or a closed (i.e., collapsed) configuration. To shape a selected end of an exhaust tube, the tool may be inserted into the tube either in its open or closed configuration. However prior to shaping the tube end, the tool is set to its open, extended configuration. Thereafter, heat is supplied to the tube end until the tube is rendered malleable. When the tube is rendered malleable, the exterior of the tube may be either manually compressed by means of a paddle or a mold may be applied to the exterior of the tube pushing the inner surface of the tube against the exterior surface(s) of the extended tool. The inner surface of the tube will then generally conform to the exterior shape of the extended tool. Thus, in apparatus according to the invention, since the internal mold defines the desired internal shape, many different external shaping means may be employed and the examples of external shaping means discussed below are merely illustrative.

In accordance with another aspect of the invention, a non-collapsible, oblate, cone-like mold may be inserted via one end of the tube and positioned, within the tube, at the tube end to be shaped. The tube end to be shaped can then be heated until the tube end is malleable and the tube can then be shaped manually, or with a mold. After shaping, the mold is removed via the one end of the tube.

The proposed method of controlling the inner surface of the tube during shaping is more robust than the current paddle method and results in a more accurately dimensioned and consistently dimensioned exhaust tube. The proposed method is less labor intensive and maintenance intensive than the prior art method and will result in yield improvements and cost reductions.

BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings like reference characters denote like components; and

FIGURE 1A is an isometric diagram of a starter tube connected to an exhaust tube shaped in accordance with the invention;

FIGURE 1B is a cross sectional diagram of the exhaust and starter tubes of Fig. 1A;

FIGURE 2 is a cross sectional diagram of one end of an exhaust tube in which is mounted a tool embodying the invention;

FIGURE 3 is a cross sectional diagram of the shaped end of an exhaust tube in which is mounted a collapsed tool embodying the invention;

FIGURE 4 is an isometric diagram of a portion of a tool embodying the invention in its extended configuration;

FIGURES 5A, 5B and 5C illustrate the shaping of an exhaust tube using an internal mold embodying the invention and an external mold;

FIGURE 6 illustrates another system for shaping an exhaust tube using an internal mold embodying the invention and an external mold; and

FIGURE 7 is a cross-section of an exhaust tube with a non-collapsible internal mold.

DETAILED DESCRIPTION OF THE INVENTION

Referring to Figs. 1A and 1B there is shown an isometric and a cross sectional diagram, respectively, of a "preform" tube 8, where the term "preform", as used herein and in the appended claims, refers to the combined, unitary, structure of a starter tube 10 and an exhaust tube 12. The starter tube 10 is a long cylindrical glass tube in which fiber optic layers are deposited to form the fiber optic strands. The exhaust tube, 12, is also a long cylindrical glass tube having, generally, and for most of its length, a larger diameter than tube 10. Tube 12 is preferably made with a larger diameter than tube 10 so that the gases escaping from tube 10 into tube 12 which get deposited along the inner walls of tube 12, particularly near the interface with tube 10, do not result in a build up which would block the passage of the gases. Also, a smooth transition to an

increasing diameter allows for well controlled, more uniform flow of the gases and reactants. Therefore, tube 12 is connected to the starter tube 10 to allow gases to escape from the starter tube in a controlled manner. When the preform 8 is used in the manufacture of optic fibers, reactants and gas vapors are introduced into the end 11 of starter tube 10. The unused gases and vapors escape from the starter tube 10 at the end 13. It is important that the "excess" gases flowing out of the starter tube 10 into the exhaust tube 12 do so with as little turbulence as possible. Reducing turbulence helps ensure that the optic fiber layers are deposited more uniformly within the starter tube. To reduce turbulence, the exhaust tube 12 is preferably designed to have a larger diameter than the starter tube and to present no sharp curves or steps at the starter/exhaust tube interface. Furthermore, it is desirable that the exhaust tube be connected to the starter tube such that its center line (cl12) lies along an extension of the center line (cl10) of the starter tube. This ensures that, when the preform is subsequently mounted in an apparatus to form optic fibers, the preform will rotate uniformly and evenly. The exhaust tube 12 is also designed to have a larger diameter than starter tube 10 to ensure that gases escaping from the starter tube and deposited along the inner surfaces of the exhaust tube do not unduly narrow the path for the escaping gases.

To mold the inner surface of the exhaust tube 12, a tool, or mold, 100 embodying the invention is inserted into one end of the tube, as shown in Fig. 2. The tool includes prongs 24a, 24b, pivotally mounted, via pivots 25a, 25b, on a sleeve, or handle, 27, which is fixedly connected (e.g., welded) to a mounting

plate 29. An anvil 33 mounted within sleeve 27 is connected to an air cylinder 31 which controls the back and forth movement of the anvil. The anvil 33 includes pockets 35a, 35b, formed between a head portion 37 of the anvil 33 and the body of the anvil, for forcing the prongs 24a, 24b, into an extended ("open") configuration and holding them fixedly in place in the open state when the anvil is urged forward by air cylinder 31. The head 37 of anvil 33 may be positioned within the tube 12, beyond the opening 13 of the tube end. The anvil 33 and head 37 when retracted cause the prongs 24a, 24b, to be rotated downward to a collapsed position, whereby the prongs are driven to the collapsed or closed configuration. In the collapsed condition, as shown in Fig. 3, the prongs occupy (i.e., encompass) a smaller volume (cylindrical, rectangular or cubic) which enables the collapsed tool to be retracted or withdrawn easily through the narrowed tube opening 13.

Thus in accordance with the invention, a tool 100 includes a molding portion (i.e., extended prongs 24a, 24b) which is inserted into the end of the exhaust tube 12 to be shaped. The tool 100 may preferably have three or more extensions (prongs or fingers 24a, 24b, 24c) which are inserted into the tube end. The prongs are mechanically attached to a handle 27 and are in a closed or collapsed configuration (as shown in Fig. 3) when withdrawn from the tube after the tube end 13 has been narrowed. The tool 100 may be activated by means of an air cylinder or a motor, as indicated in the figures, or by means of a manual spring-loaded mechanism or any other suitable means. The tool is operated such that the prongs or fingers may be extended

upwardly and outwardly (as shown in Figs. 2 and 4) so that they can open and the external surfaces of the prongs can press against (or be pressed against by) the inside surface of the exhaust tube 12, when the tube 12 is rendered malleable. The tube 12 may be rendered malleable by the application of a heat source, such as torch 16, to the tube end being shaped. After being rendered malleable, pressure may be applied to the exterior end surface of the tube 12 causing the inner surface of the selected end of tube 12 to be compressed together and the end narrowed, as shown in Fig. 3. The tool 100 may be inserted into the tube 12 while the tool 100 is in the collapsed condition. However, depending on tolerances of the various components, the tool 100 may also be inserted into the tube while the prongs are in the extended configuration.

The tool 100 should be constructed of temperature resistant materials (e.g., graphite, ceramic). The mold components may be manufactured to close tolerances from materials which can withstand the high temperatures of molten glass. Examples of appropriate materials include cast iron or steel coated with a ceramic or other coating resistant to the high temperatures. It is important that any ceramic coating used will not contaminate the glass products being manufactured.

The prongs or fingers (e.g., 24a, 24b, 24c), which may be pivoted via pivots (e.g., 25a, 25b) from a closed to an open (extended) configuration (or vice-versa), are designed to have substantial width, such that when in the open or extended condition the prongs arranged side-by-side, as shown in Fig. 4, cover

00162080582950

a significant portion of the inner tube circumference. The exterior surfaces (e.g., 241a, 241b) of the prongs, when opened, as shown in Fig. 4, also define the shape which it is desired to impart to the inner surface of the tube 12. The prongs in this extended condition define the cross sectional profile to be imparted to the inner tube surface. (The prongs may also be characterized as a multi-segmented spring structure with the number of segments varying from 3 to 15, or more.) Thus, the exterior surfaces 241a, 241b of the tool 100, when opened, function as an internal mold against which the inner surface of the tube 12 may be shaped using either a paddle or an external mold. That is, after the tool is inserted into the tube 12 and after the tool is set to its extended condition, the end of tube 12 being shaped may be heated by a torch 16 (See Figs. 2 and 5A) or like heat source (See Fig. 6) until the tube 12 is rendered malleable. A paddle 40 (see Fig. 2) may then be used to shape the tube end so that the tube end is caused to become narrower with the inside surface of the tube conforming to the exterior surface of the prongs of tool 100. Alternatively, a multi-piece external mold may be applied to the exterior of the tube 12 (as shown in Figs. 5A, 5B, 5C and 6) to shape the selected end region of tube 12 in conjunction with the interior mold 100 set to its extended condition. After the tube is shaped and cooled the tool may be returned to its collapsed condition and the prongs removed through the narrowed tube end of the tube 12.

In systems embodying the invention, it is not necessary to inject air into the tube cavity to achieve and maintain the desired tube shape. Also, it is not necessary to insert a plug into the tube end since the tool 100 serves to

physically support the inside of the tube cavity and at the same time provide the proper shape against which the tube, when rendered malleable, is pressed.

Fig. 3 illustrates that, when in the closed configuration, the tool can be easily retracted through the narrowed opening of the formed tube end. Note that the tool 100 can be inserted into the tube when it is in its closed configuration. However, it should be understood that the tool 100 can also be inserted into the tube 12 while set to its open, extended condition.

Fig. 3 shows the prongs in their closed position. Fig. 3 also shows the air cylinder system 45 to retract the anvil assembly fixture on which is held the mounting plate 29 and to which is connected the air cylinder assembly 31 to control the advance and retraction of the anvil 33.

As shown in Figs. 2 and 3, prongs or fingers 24a, 24b are pivotally mounted on a sleeve 27 which is fixedly connected (e.g., welded) to a mounting plate 29. An air cylinder 31 is shown connected to an anvil 33 mounted within sleeve 27. The exterior surfaces 241a, 241b of prongs 24a, 24b, when extended, defines the shape of the surface which the inner surface is to acquire when formed. During the forming process, the tube 12 would be mounted on a lathe (See Fig. 5A or 6) to enable the tube to be rotated. The tool 100 would then be inserted into the end of the tube to be shaped. The tool 100 may be inserted in its collapsed form or in its open form. If inserted in its collapsed form, the tool 100, after being inserted, would be opened to its extended state. Heat would then be applied to the tube 12, as shown in Figs. 2, 5A or 6, to render the selected tube end malleable. When that condition is reached, a mallet or

paddle (40 in Fig. 2) may be used to manually compress and press against the end of the tube 12 to cause the end of the tube to be narrowed, while the inner surface of the tube conforms closely to the exterior shape of the prongs of the tool in their extended (open) configuration.

Referring to Fig. 5A, there is shown an apparatus for semi-automatically, or automatically, shaping a selected end 121 of the tube. Tube 12 is firmly positioned within a central opening 64 of a rotatable chuck 62 of a horizontally mounted controlled speed lathe 60. The lathe 60 supports tube 12 and ensures that tube 12 is rotated at a controlled speed. The internal mold 100 and prongs 24 may be inserted into the selected end of tube 12, as discussed above and as illustrated in Figs. 2, 3 and 4. A heat source 16 is positioned such that the selected end portion, 121, of tube 12 is heated to a temperature of, for example, approximately 2,100 degrees centigrade, which causes the end of the tube to become soft and malleable. The heat source 16 may be an oxygen-hydrogen torch, but any other suitable heat source may be used. Figures 5B and 5C illustrate the application of an external mold assembly to a tube 12 while the internal mold 100 with prongs 24 is inserted within the tube. This arrangement enables the shaping of tube 12 in a semi-automatic manner. The temperature of the heat source applied to the tube can be measured by a pyrometer 80 having an output 81 which can be coupled to control circuitry 91 for controlling the heat supplied to the tube end, 121. The output of pyrometer 80 may also be used to control the application and retraction of the heat source, 16. The heat source 16 may be moved back and forth via a motor 65 which may be controlled by an

of the pyrometer, may be used to sense the condition (e.g., the malleability) of the tube in order to apply and or retract the external mold.

When the tube is heated to the point that it is rendered soft and malleable, the torch 16 may be turned off and/or moved out of the way. The two side sections 22a and 22b of the mold are applied around the periphery of tube 12, along its selected tail end portion 12, for imparting a smooth curve to the tail end of the tube. The two side pieces 22a, 22b, leave an opening at their end surrounding the sleeve 27 supporting the prongs 24. Prongs 24 are preferably inserted within the opening of tube 12, prior to the application of heat to the tube end, for shaping the inner surface of tube 12 and ensuring the proper dimensioning of the inner diameter of tube 12, as discussed above. Thus, the prongs 24, in combination with the side mold pieces, 22a,22b, impart a predetermined shape to the inner surface and to the inner rim of tube 12 and also controls the inner and outer diameters of tube 12, to enable a starter tube to “nest” and/or mate within the opening of the exhaust tube 12.

After the tube is formed and the system has stabilized, the external mold pieces 22a, 22b are retracted from the tube. Concurrently, the tool 100 and prongs 24 are withdrawn from within the tube and the exhaust tube is allowed to cool. That is, after the internal and external mold pieces have been applied for a predetermined period for shaping the exhaust tube, the molding components 22a, 22b, and 24 are retracted to allow the glass tube to cool and to then be removed from the equipment.

The apparatus of Figs. 5A, 5B and 5C may be part of a semi-automatic or automatic system for molding and shaping a selected end of the exhaust tube to mate with the starter tube.

Thus, according to one aspect of the invention, exhaust tube 12 may be shaped semi-automatically or automatically, with a simple, closed loop, control system. This eliminates the "art" used in the prior art forming method and replaces it with a method and apparatus for forming tubes having more consistent form dimensions, with fewer defects and fewer unusable products. Consequently, the manufacture of exhaust tubes and preforms in accordance with the invention leads to increased productivity in the manufacture of optical fibers.

Thus, in accordance with the invention, glass tubes may be formed which have reproducible dimensions and consistently have the same shape resulting in a reduced number of defective products and eliminating the need for manually forming the glass tubes.

As shown in Figs. 5B and 5C, the external mold pieces include elongated side sections 22a, 22b. The side sections 22a and 22b are applied along an end section of tube 12, extending from a point 127, past the bending point 125, and past the end 13 of tube 12. The side sections impart a smooth taper to the end section of the tube 12 and reduce its inner diameter gradually such that at a point 13, the inner diameter of tube 12 matches that of a starter tube 10, intended to be mated with tube 12. The resulting end section of tube 12 may be generally characterized as an oblate

cone like section. The prongs 24 inserted into the orifice at the selected end of hollow cylindrical tube 12 shape the inner rim of the tube end and prevent the inner diameter of the tube 12 from decreasing below a predetermined value. The portion of tube 12 squeezed between the inner surfaces of mold pieces 22a, 22b and the outer surfaces of the prongs 24i results in tube 12 assuming a desired shape. The application of the external mold pieces, 22a, 22b, together with internal mold pieces 24, to a selected end of tube 12, after it has been rendered malleable, causes tube 12 to assume the desired form.

. Figure 5B also shows that the two side pieces of the mold, 22a and 22b, are held by mechanical holding arms 51a, 51b, which may be selectively activated by air cylinders 31a, 31b, to cause the application and/or retraction of the side molds 22a, 22b to, or from, the cylindrical tube 12. The two side pieces of the mold may originally be part of a unitary sleeve-like structure which is cut (sawed) in half (or in a different ratio) to produce the two halves 22a, 22b. The outer periphery of the two side pieces may include studs or holding holes or posts to enable holding arms 51a, 51b to securely hold and apply their respective mold section.

Figure 5C is a simplified cross sectional diagram showing the general shape of tube 12 after the external mold pieces 22a, 22b have closed-in on the tube. The side pieces, 22a and 22b, extend along the length of cylindrical tube 12 and impart a smooth taper along the length of the tube beginning at a point 125 and continuing to the end 13 of the tube. When joined together, the inner surfaces of side pieces 22a, 22b define an oblate cone-like shape. In their

application, the side pieces extend from a point 127 along the tube 12 to the end 13 of the tube to complete shaping the end of tube 12. The prongs 24 ensure that the shape of the inner surface and the opening 13 at the mating end of tube 12 are as desired.

The opening of tube 12 needs to be sufficiently large to ensure that the inner diameter of the "shrunk" exhaust tube at point 13 is approximately equal to the inner diameter of starter tube 10 while the outer diameter of tube 12 between lines 13 and 14 is just a little larger than the outer diameter of starter tube 10. This enables the starter tube to be easily mated into the opening of tube 12.

Fig. 6 illustrates that the system of Fig. 5A may be modified such that at least one of the mold pieces 22b contains a heat source (gas source 601 connected to gas fitting 603 connected to gas tubing 605 connected to mold 222b) for applying heat to the tube end. The external mold 222a, 222b in Fig. 6 contain a heat source and also function to shape the external portion of the tube and to compress end portion 121 of the tube 12 so that its inner surface conforms to the exterior surface of extended prongs 24.

Although a particular embodiment has been described, it is to be understood that the present disclosure is only by way of illustration and that numerous changes in the shape of the tubes and in the construction of the molds may be made without departing from the spirit and scope of this invention.

Thus, an important aspect of the invention is that a first internal mold 100, including prongs 24, is used to shape the inner surface of the tube 12. Applicants

recognized that controlling the shaping of the inner surface of tube 12 is most important to produce the required predetermined form. In the system of Figs. 2, 3, 4, 5 and 6, in order to withdraw the inner mold 100 after the tube is shaped (and its opening narrowed) the inner mold (prongs 24) must be collapsed and the volume of the prongs must be reduced to enable the mold to be extracted from the narrowed end of the tube.

However, when tolerances of the inner diameter of the tube 12 permit, it may be possible to push (or pull) the internal mold through the opposite (non-narrowed) end of the exhaust tube 12 and eliminate the need to collapse the mold for extraction. To accomplish this, internal mold 100 would have to be made so it can be detached from anvil 33 or sleeve 27.

Alternatively, when the tolerances permit, it may be appropriate to construct a fixed, preshaped, internal mold 240 and mount it on a rod or shaft 71 which can extend the length of the exhaust tube, as shown in Fig. 7. The rod 71 may be supported by one or more shims 73 for holding the rod 71 steady within the tube during insertion, extraction and shaping of the selected tube end. The mold may be inserted from either end of the tube. The tube may be shaped by applying heat to the selected tube end via torch 16 and, when the tube end is softened, applying an external mold (e.g., 22a, 22b) or manually working the tube. Then, after the inner surface of the selected tube end is shaped to conform to the outer surface of the internal mold 240, it may be withdrawn from the non-narrowed end of the tube 12, after the tube is shaped.

Certain mold configurations have been shown, but it should be understood that many variations and modifications may be made without departing from the spirit and scope of the inventive aspects of the molds to shape tubes.

WHAT IS CLAIMED IS:

1. Apparatus for shaping a selected end region of a hollow cylindrical glass tube used in the manufacture of optic fibers comprising:
 - a support means for holding the tube at a second region, other than the selected end region, for rotating the tube in a controlled manner;
 - a heat source adapted to supply sufficient heat to the selected end region of the tube to render it malleable;
 - an internal mold for supporting and shaping the inner surface of the selected region of the tube, when the tube is rendered malleable;
 - means for inserting said internal mold within said selected end region of the tube, prior to the application of heat to the tube; and
 - means for compressing the exterior surface of the selected end region of the tube and for shaping the exterior surface of the selected end region of the tube, when rendered malleable, and for, concurrently, causing the shape of the inner surface of selected end region of the tube to conform to the exterior surface of the internal mold.
2. An apparatus as claimed in claim 1 wherein said internal mold may be selectively altered so it can assume an open, extended, configuration or a closed, collapsed, configuration.
3. An apparatus as claimed in claim 2 wherein said means for inserting said internal mold within said selected end region of the tube includes:
 - (a) means for setting the mold to its extended configuration, and (b)
 - means for setting the internal mold to its collapsed configuration for

056228908 "07.31.00

withdrawing the mold from the tube through an opening in the selected end region.

4. An apparatus as claimed in claim 3, wherein setting the internal mold to its collapsed configuration causes the internal mold to occupy a small volume in order to enable the mold to be easily retracted from the selected tube end.
5. An apparatus as claimed in claim 1, wherein the means for compressing the exterior surface of the selected end region of the tube and for shaping the exterior surface of the selected end region of the tube includes manual means for shaping the exterior end region of the tube.
6. An apparatus as claimed in claim 1, wherein the means for compressing the exterior surface of the selected end region of the tube and for shaping the exterior surface of the selected end region of the tube includes an actuatable mechanical holding means for holding an exterior mold and for selectively applying the exterior mold to the outer periphery of the selected end region of the tube, when the tube is rendered malleable, for shaping the exterior of the selected end region

of the tube while the internal mold supports the inner walls of the tube and controls the shape of the inner diameter of the tube.

7. Apparatus for shaping a selected end region of a hollow cylindrical glass tube used in the manufacture of optic fibers comprising:

a support means for holding the tube at a second region, other than the selected end region, for rotating the tube in a controlled manner;

a mold for shaping the inner surface of the selected end region of the tube, said mold being selectively settable to an open, extended configuration or a closed, collapsed, configuration;

means for inserting said variable configuration mold within said selected end region of the tube and for setting the mold in its extended configuration; said mold, when inserted in the selected end of the tube and when in its extended configuration, for shaping the inner surface of the selected end region of the tube;

a heat source adapted to supply sufficient heat to the selected end region of the tube to render it malleable; and

means for compressing the exterior surface of the selected end region of the tube, when rendered malleable, and for, concurrently, causing the shape of the inner surface of the tube to conform to the exterior surface of the molding means.

8. An apparatus as claimed in claim 7 wherein said means for inserting said mold within said selected end region of the tube also includes means for setting the mold to its collapsed configuration for

withdrawing the mold from the tube through an opening in the selected end region.

9. An apparatus as claimed in claim 8, wherein setting the variable configuration mold to its collapsed configuration causes the mold to occupy a small volume to enable the mold to be easily withdrawn from, and through, the narrowed selected end region of the tube.
10. An apparatus as claimed in claim 9, wherein said means for compressing the exterior surface of the selected end region of the tube includes an actuatable mechanical holding means for holding a multi piece exterior shaping mold for selectively applying the exterior shaping mold to the selected end region of the tube, when the tube is rendered malleable, for shaping the selected end region of the tube in conjunction with the variable configuration mold.
11. An apparatus as claimed in claim 10, wherein said exterior shaping mold includes two side pieces for imparting an oblate, cone-like shape to the inner and outer diameters of the tube along its selected end region while leaving an opening between the mold pieces for enabling the withdrawal of the variable configuration mold when set to its collapsed condition.
12. An apparatus as claimed in claim 11 further including sensing means for sensing the temperature of the selected end region of the tube.
13. An apparatus as claimed in claim 12 wherein the temperature sensing means is a pyrometer producing an actuating signal coupled to the

actuatable mechanical holding means when the temperature of the selected end portion is such that the end portion is in a malleable state.

14. An apparatus as claimed in claim 13 wherein the heat source is a torch and wherein said actuating signal produces a signal for removing the torch when the exterior shaping mold is applied to the selected end portion of the tube.
15. An apparatus as claimed in Claim 14 wherein said sensing means for sensing the temperature controls the intensity of the heat source applying heat to the selected end portion of the tube.
16. An apparatus as claimed in Claim 8 wherein the tube is a first tube and wherein the variable configuration mold and the exterior shaping mold shape the opening of the first tube to enable a second tube to be inserted snugly within the first tube, while the first and second tubes can be easily aligned to have a common center line.
17. An apparatus as claimed in Claim 7, wherein the support means is a lathe.
18. An apparatus as claimed in Claim 7 further including optical sensing means for sensing the condition of the tube.
19. A method for shaping a selected end of a hollow cylindrical tube comprising the steps of:

positioning the tube within a support means and rotating the tube;

inserting an internal mold within the selected end region of the tube to support the tube end when the tube is being shaped and for controlling the shape of the inner surface of the tube end;

heating the selected end of the tube with a heat source until the selected end becomes malleable; and

compressing the exterior surface of the selected end region of the tube for concurrently shaping the exterior and inner surfaces of the selected end region of the tube into a predetermined form.

20. A method as claimed in claim 19, wherein the internal mold is settable to an extended, open, configuration or to a collapsed, closed, configuration, and wherein the step of inserting the internal mold includes the step of setting the mold to its open configuration before and during the time heat is applied to the selected end of the tube.

21. A method as claimed in claim 20, wherein the step of compressing the exterior surface of the selected end region of the tube for concurrently shaping the exterior and inner surfaces of the selected end region of the tube includes the step of applying an external mold to the selected end of the tube when the end segment becomes malleable.

22. A method for shaping the opening and end region at a selected end of a cylindrical tube comprising the steps of:

[illegible][illegible][illegible][illegible][illegible]

[illegible][illegible]




FIG 1A




FIG-2

FIG 2






FIG 3





310




FIG 5B





FIG 5C






Fig 7

Declaration and Power of Attorney

Our residence, post office address and citizenship are as stated below next to our names.

We hereby state that we have reviewed and understand the contents of the above identified specification, including the claims, as amended by an amendment, if any, specifically referred to in this oath or declaration.

We acknowledge the duty to disclose all information known to us which is material to patentability as defined in Title 37, Code of Federal Regulations, 1.56.

We hereby claim foreign priority benefits under Title 35, United States Code, 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

None

We hereby claim the benefit under Title 35, United States Code, 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code 112, we acknowledge the duty to disclose all information known to us to be material to patentability as defined in Title 37, Code of Federal Regulations, 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

None

We hereby declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

We hereby appoint the following attorney(s) with full power of substitution and revocation, to prosecute said application, to make alterations and amendments therein, to receive the patent, and to transact all business in the Patent and Trademark Office connected therewith:

Thomas J. Bean	(Reg. No. 44,528)
Lester H. Birnbaum	(Reg. No. 25,830)
Richard J. Botos	(Reg. No. 32,016)
Jeffery J. Brosemer	(Reg. No. 36,096)
Kenneth M. Brown	(Reg. No. 37,590)
Donald P. Dinella	(Reg. No. 39,961)
Guy Eriksen	(Reg. No. 41,736)
Martin J. Finston	(Reg. No. 31,613)
William S. Francos	(Reg. No. 38,456)
Barry H. Freedman	(Reg. No. 26,166)
Julio A. Garceran	(Reg. No. 37,138)
Jimmy Goo	(Reg. No. 36,528)
Anthony Grillo	(Reg. No. 36,535)
Stephen M. Gurey	(Reg. No. 27,336)
John M. Harman	(Reg. No. 38,173)
Matthew J. Hodulik	(Reg. No. 36,164)
Michael B. Johannesen	(Reg. No. 35,557)
Mark A. Kurisko	(Reg. No. 38,944)
Irena Lager	(Reg. No. 39,260)
John B. MacIntyre	(Reg. No. 41,170)
Christopher N. Malvone	(Reg. No. 34,866)
Scott W. McClellan	(Reg. No. 30,776)
Martin G. Meder	(Reg. No. 34,674)
John C. Moran	(Reg. No. 30,782)
Michael A. Morra	(Reg. No. 28,975)
Gregory J. Murgia	(Reg. No. 41,209)
Claude R. Narcisse	(Reg. No. 38,979)
Joseph J. Opalach	(Reg. No. 36,229)
Neil R. Ormos	(Reg. No. 35,309)
Eugene E. Pacher	(Reg. No. 29,964)

007E20 80692960


09628508 0733100

Jack R. Penrod	(Reg. No. 31,864)
Gregory C. Ranieri	(Reg. No. 29,695)
Scott J. Rittman	(Reg. No. 39,010)
Ferdinand M. Romano	(Reg. No. 32,752)
Eugene J. Rosenthal	(Reg. No. 36,658)
Bruce S. Schneider	(Reg. No. 27,949)
Ronald D. Slusky	(Reg. No. 26,585)
David L. Smith	(Reg. No. 30,592)
Ozer M. N. Teitelbaum	(Reg. No. 36,698)
John P. Veschi	(Reg. No. 39,058)
David Volejnicek	(Reg. No. 29,355)
Charles L. Warren	(Reg. No. 27,407)
Jeffrey M. Weinick	(Reg. No. 36,304)
Eli Weiss	(Reg. No. 17,765)

We hereby appoint the attorney(s) on ATTACHMENT A as associate attorney(s) in the aforementioned application, with full power solely to prosecute said application, to make alterations and amendments therein, to receive the patent, and to transact all business in the Patent and Trademark Office connected with the prosecution of said application. No other powers are granted to such associate attorney(s) and such associate attorney(s) are specifically denied any power of substitution or revocation.

Full name of first joint (sole) inventor:

Inventor's signature


Jason A. Kay

Date

7/15/00

Residence: ~~41 Mt. Kemble Ave., Morristown, NJ 07960~~

Citizenship: USA


45 Chatham Ct., Robbinsville, NJ 08691

Post Office Address:

~~41 Mt. Kemble Ave., Morristown, NJ 07960~~

Full name of second joint inventor:

Inventor's signature


David S. Kerr

Date

7/12/00

Residence: 2 Walsh Way, Morris Plains, NJ 07950

Citizenship: USA

Post Office Address: 2 Walsh Way, Morris Plains, NJ 07950



Full name of third joint inventor:

Inventor's signature *Peter M. Mueller* Date 7/26/00
Peter M. Mueller

Residence: 4584 Campenille Trace, Suwanee, GA 30024

Citizenship: USA

Post Office Address: 4584 Campenille Trace, Suwanee, GA 30024

Full name of fourth joint inventor:

Inventor's signature *Ivan Pawlenko* Date 7-19-00
Ivan Pawlenko

Residence: 1242 Old Jordan Road, Holland, PA 18966

Citizenship: USA

Post Office Address: 1242 Old Jordan Road, Holland, PA 18966

Full name of fifth joint inventor:

Inventor's signature *Larry Samson* Date 7/19/00
Larry Samson

Residence: 34 Polder Drive, Langhorne, PA 19053

Citizenship: USA

Post Office Address: 34 Polder Drive, Langhorne, PA 19053

0963808 07100

ATTACHMENT A

Attorney Name Henry I. Schanzer, Esq.
Michael Y. Epstein, Esq.

Reg. No. 25,219

Reg. No. 21,186

Telephone calls should be made to Henry I. Schanzer at :

Phone No.: (732) 572-3984

Fax No.: (732) 572-3653

All written communications should be addressed to:

Henry I. Schanzer, Esq.
29 Brookfall road
Edison, NJ 08817

001220 80582950